

PLAGLAS®	PRODUCT	Polycarbonate Flame Retardancy Sheet / Roll
	GRADE	PC-FR-TR
	THICKNESS	3.0~10.0mm

It contains UL94 V-0 grade from UL and free from environmental contamination

Properties	Test method	Condotion	Unit	Value
PHYSICAL PROPERTIES				
Specific gravity	ASTM D792	Natural	-	1.2
Water absorption	ASTM D570	23°C,24hr	%	0.58
Refracctive index	ASTM D542	-	-	1.59
OPTICAL PROPERTIES				
Light Transmittance	ASTM D1003	-	%	87
HAZE	ASTM D1003	-	%	3
Yellowness index	ASTM D1925	Less than	%	2
MECHANICAL PROPERTIES				
Tensile strength	ASTM D638	50mm/min	Mpa	65
Tensile strain	ASTM D638	50mm/min	%	115
Flexural strength	ASTM D790	2.8mm/min	Mpa	100
Flexural Modulus	ASTM D790	2.8mm/min	Mpa	2350
Izod impact strength	ASTM D256	3.2mm	KJ/m ²	85
Charpy impact strength	ASTM D6110	3.0mm	KJ/m ²	82
Rockwell hardness	ASTM D785	-	R Scale	118
THERMAL PROPERTIES				
Heat deflection temperature	ASTM D648	1.8Mpa	°C	144
Heat deflection temperature	ASTM D648	0.45Mpa	°C	139
Linear expansion coefficient	ASTM D696	-	cm/cm/°C	6.8×10 ⁻⁵
Vicat softening Temperature	ISO 306	B/50	°C	145
Flammabilty	UL94	3mm	-	V-0

Certificate		
	Certificate	Test result