

# Greenhouse Cover

**TAJO®**

## TAJO® 3-Layer Long JANGSOO

Film usage	Greenhouse cover
Width-meter	Up to 16
Thickness-Micron	Up to 200
Length	As required
Color	Clear(Blue)



Test items		Test Method	Units	Values
Tensile strength	MD	ASTM D882	MPa	25
	TD		MPa	23
Elongation	MD		%	570
	TD		%	680
Tear resistance	MD	ASTM D1922	g/mm	11200
	TD		g/mm	12000
Drop dart impact	A method	ASTM D1709	g	750
Light transmission in PAR		ASTM D1003	%	86
Diffused light transmission in PAR			%	20
Light transmission in IR	Thermal		%	45
Anti drip	Place in accordance to instruction			Yes
Anti mist	Place in accordance to instruction			Yes

Typical values



**TAJO®**  
Greenhouse Cover Film

**TAEKWANG NEWTEC Co., Ltd.**

16, Seonyu-ro9-gagil, Yeongdeungpo-gu, Seoul, Korea **Tel** +82-2-3662-2367 **Fax** +82-2-3661-7513

**Web site** <http://www.plastar.co.kr> **Email** taekwang@plastar.co.kr