

Greenhouse Cover

TAJO®

TAJO® HD Black Mulching



Film usage	Soil cover film
Width-meter	Up to 1.5
Thickness-Micron	Up to 20
Length-meter	500, 1000

Test items		Test Method	Units	Values
Tensile strength	MD	ASTM D882	MPa	55
	TD		MPa	45
Elongation	MD	ASTM D882	%	380
	TD		%	430
Tear resistance	MD	ASTM D1922	g/mm	1500
	TD		g/mm	25000
Drop dart impact	A method	ASTM D1709	g	-
Light transmission in PAR		ASTM D1003	%	-
Diffused light transmission in PAR			%	-
Light transmission in IR			%	-
Anti drip		-		-
Anti mist		-		-

Typical values



TAJO®
Greenhouse Cover Film

TAEKWANG NEWTEC Co., Ltd.

16, Seonyu-ro9-gagil, Yeongdeungpo-gu, Seoul, Korea **Tel** +82-2-3662-2367 **Fax** +82-2-3661-7513

Web site <http://www.plastar.co.kr> **Email** taekwang@plastar.co.kr