

# Greenhouse Cover

**TAJO®**

## TAJO® PO COATING - GREENHOUSE

Film usage	Greenhouse cover
Width	Above 9.2m is seamed
Thickness-Micron	80, 100, 120, 150
Length	As required



Test items		Test Method	Units	Values
Tensile strength	MD	ASTM D882	MPa	30
	TD		MPa	28
Elongation	MD		%	550
	TD		%	650
Tear resistance	MD	ASTM D1922	g/mm	12700
	TD		g/mm	13500
Drop dart impact	A method	ASTM D1709	g	850
Light transmission in PAR		ASTM D1003	%	89
Diffused light transmission in PAR			%	18
Light transmission in IR			%	32
Anti drip		Super-hydrophilic nano-coating		Yes
Anti mist		Super-hydrophilic nano-coating		Yes

Typical values



**TAJO®**  
Greenhouse Cover Film

**TAEKWANG NEWTEC Co., Ltd.**

16, Seonyu-ro9-gagil, Yeongdeungpo-gu, Seoul, Korea **Tel** +82-2-3662-2367 **Fax** +82-2-3661-7513

**Web site** <http://www.plastar.co.kr> **Email** taekwang@plastar.co.kr