

Greenhouse Cover

TAJO®

TAJO® PREMIUM GOLD

Promote the photosynthesis activity of the plants



Film usage	Greenhouse cover
Width-meter	Up to 16
Thickness-Micron	Up to 200
Length	As required

Test items		Test Method	Units	Values
Tensile strength	MD	ASTM D882	MPa	25
	TD		MPa	23
Elongation	MD		%	600
	TD		%	680
Tear resistance	MD	ASTM D1922	g/mm	9500
	TD		g/mm	11500
Drop dart impact	A method	ASTM D1709	g	650
Light transmission in PAR		ASTM D1003	%	89
Diffused light transmission in PAR			%	16
Light transmission in IR			%	35
Anti drip	Place in accordance to instruction			Yes
Anti mist	Place in accordance to instruction			Yes

Typical values



TAJO®
Greenhouse Cover Film

TAEKWANG NEWTEC Co., Ltd.

16, Seonyu-ro9-gagil, Yeongdeungpo-gu, Seoul, Korea **Tel** +82-2-3662-2367 **Fax** +82-2-3661-7513

Web site <http://www.plastar.co.kr> **Email** taekwang@plastar.co.kr